BLUE RIVER | FINISHES







Honed Finish



Polished Finish



Antique Brush Finish



Bushhammer Finish



Thermal Finish

ASTM SPECIFICATIONS

ASTM C 97

SPECIFIC GRAVITY: 2.55 ABSORPTION: 2.66%

ASTM C 99

MODULUS OF RUPTURE: 1,866 lb/in²

ASTM C 170

COMPRESSIVE STRENGTH: Perpendicular Area 9.45 in² 13,350 psi Parallel Area 9.54 in² 12,800 psi

ASTM C 880

FLEXURAL STRENGTH: Parallel to the Rift/Dry: 1,748 psi