


BRENTWOOD | FINISHES



Sawn Finish



Honed Finish



Polished Finish



Antique Brush Finish



Bushhammer Finish

ASTM SPECIFICATIONS

ASTM C 97

DENSITY: 151.55 lb/ft³

SPECIFIC GRAVITY: 2.429

ABSORPTION: 1.81%

CLASS II QUARTZITIC SANDSTONE

CLASS III QUARTZITE

ASTM C 99

MODULUS OF RUPTURE: 1,554 psi

CLASS III QUARTZITE

10.71 Mpa

ASTM C 170

COMPRESSIVE STRENGTH: 11,403 psi

CLASS III QUARTZITE

78.61 Mpa

ASTM C 241

ABRASION RESISTANCE: 52.58

CLASS III QUARTZITE

ASTM C 880

FLEXURAL STRENGTH:

Perpendicular: 3,065 psi

Parallel: 21.13 Mpa